

VERSI-FOAM® Systems I, 15 and 50 Disposable Foam Kit

RHH FOAM SYSTEMS, INC.
6001 South Pennsylvania Avenue
Cudahy WI 53110 USA
Telephone: 1-800-657-0702
 414-744-6066
FAX: 414-744-8227
E-Mail: sales@rhhfoamsystems.com
Web Site: www.rhhfoamsystems.com

VERSI-FOAM® Systems I, 15 and 50 are disposable foam kits that contains two chemical components - Component A (isocyanate) and Component B (polyol blend); patented U-CONTROL dispensing gun, ten (10) multi-purpose mixing nozzles, and packet of petroleum jelly. It requires no external power source.

VERSI-FOAM Systems I, 15 and 50 have the following physical properties:

DENSITY:	1.75 pounds per cubic foot, free rise	ASTM D1622
R FACTOR:	7.69	ASTM C177
COMPRESSIVE STRENGTH:	22.1 psi (parallel)	ASTM D1621
SHEAR STRENGTH:	36.6 psi (parallel)	ASTM C273
WATER ABSORPTION:	4.69%	ASTM D2842
CLOSED CELL CONTENT:	>97%	ASTM D2856
DIMENSIONAL STABILITY:		ASTM D2126
% Volume Change, 158° F, 2 wks	+0.44	
% Volume Change, -100° F, 2 wks	+2.90	
HIGH TEMPERATURE TOLERANCE	250° F	
LOW TEMPERATURE TOLERANCE	-250° F	
FLAMESPREAD:	N/A	ASTM E84
SMOKE DEVELOPED:	N/A	ASTM E84
YIELD:		
System I	1 cubic foot or 12 square feet at 1" thickness	
System 15	16.5 cubic feet or 198 square feet @ 1" thickness	
System 50	50 cubic feet or 600 square feet @ 1" thickness	
TACK FREE TIME:	30 seconds	
RISE TIME:	30 seconds	